

Sample card fabric expansion joints

E-GLASS FABRICS

THERMOQUA 400 T500 - N°20

Description: Filament of E-glass fibres 400 g/m²

Application: Insulation and supporting fabric. Flange reinforcement

Weight (g/m²)	400	Thermal conductivity	0,11
Thickness (mm)	0,4	Tensile strength (N/cm)	750 x 550
Temperature (°C)	500	Color	White

E-GLASS FABRICS

THERMOQUA 800 T500 - N°16

Description: Filament of E-glass fibres 800 g/m²

Application: Insulation and supporting fabric. Flange reinforcement

Weight (g/m²)	800	Thermal conductivity	0,11
Thickness (mm)	0,9	Tensile strength (N/cm)	1650 x 1650
Temperature (°C)	500	Color	White

E-GLASS FABRICS

THERMOQUA 1100 T500 - N°17

Description: Filament of E-glass fibres 1050 g/m²

Application: Insulation and supporting fabric. Flange reinforcement


Weight (g/m²)	1050	Thermal conductivity	0,12
Thickness (mm)	1,3	Tensile strength (N/cm)	2400 x 1300
Temperature (°C)	500	Color	White

Contact

DEKOMTE BENELUX BVBA

Simon Stevinstraat 8 | 8400 Oostende - Belgium | T +32 (0) 59 51 07 55 | F +32 (0) 59 51 07 87 | E info@dekomte.be





Sample card fabric expansion joints

E-GLASS FABRICS

THERMOQUA 1300 T550 - N°18

Description: Filament of E-glass fibres 1250 g/m²

Application: Insulation and supporting fabric. Flange reinforcement

Weight (g/m²)	1250	Thermal conductivity	0,12
Thickness (mm)	1,6	Tensile strength (N/cm)	1200 x 1200
Temperature (°C)	550	Color	White

E-GLASS FABRICS

THERMOQUA 2000 T550 - N°19

Description: Filament of E-glass fibres 1900 g/m²

Application: Insulation and supporting fabric. Flange reinforcement

Weight (g/m²)	1900	Thermal conductivity	0,12
Thickness (mm)	3	Tensile strength (N/cm)	1500 x 2000
Temperature (°C)	550	Color	White

E-GLASS FABRICS

THERMOTEX 1225 HT600 - N°23

Description: Filament of E-glass fibres finished on silica acid basis 1225 g/m²

Application: Insulation and supporting fabric. Flange reinforcement

Weight (g/m²)	1225	Thermal conductivity	0,15
Thickness (mm)	2,3	Tensile strength (N/cm)	850 x 1000
Temperature (°C)	600	Color	Yellow

Contact

DEKOMTE BENELUX BVBA

Simon Stevinstraat 8 | 8400 Oostende - Belgium | T +32 (0) 59 51 07 55 | F +32 (0) 59 51 07 87 | E info@dekomte.be

